PU RUI Fiber Cement Felt





ABOUT US


PURUI .One of the top fiber cement felt manufactory in china. With more than 20 years experience in fiber cement industry. we service more than 80 fiber cement company in china.

we provide Hatschek machine felt and Flow on process machine felt for FC industry. With customer demanded ,we also trade some accessroy for FC company, such as S.S wires mesh,abrasive belt etc..

E-SPEED -HATSCHEK MACHINE FELT

Basis weight	1450-1700 GSM
Base fabric weigh)	750-1000 GSM
Web weight	700 GSM
BASE : WEB	56/ 44
MD Yarn	NYLON PLIED MONO 2 layers
CD Yarn	NYLON PLIED MONO 2 layers
Batt on sheet side	17& 44 /55Dtex.
Batt on roll side	44 /55Dtex
Calliper at dry state	4-4.8 mm
Air permeability	75-90cfm
Treatment	Pre-compaction.
Elongation	About 1-1.5%
Comments: 1: Specially surface fiber provide good	

- 1: Specially surface fiber provide good adhesive property
- 2: Full speed when new felt changed
- 3: less vacuum cost
- 4: Easy to clean and long life time



PU RUI Fiber Cement Felt

E-SMOOTH -HATSCHEK MACHINE FELT


Basis weight	1700-2100 GSM
Base fabric weigh)	950 –1450 GSM
Web weight	750 GSM
BASE : WEB	AROUND 57/ 43
MD Yarn	NYLON PLIED MONO 3layers
CD Yarn	NYLON PLIED MONO 3 layers
Batt on sheet side	17& 44/55 Dtex.
Batt on roll side	44/55 Dtex
Calliper at dry state	4.5-5.2mm
Air permeability	85-110cfm
Treatment	Pre-compaction.
Elongation	About 1- 1.5%

Comments:

1: Specially base fabric for smooth property

2: Good dewatering

3: Easy to clean and long life time



PU RUI Fiber Cement Felt

E-MARK -HATSCHEK MACHINE FELT

Basis weight	1700-2100 GSM
Base fabric weigh)	1000 –1500GSM
Web weight	600-700 GSM
BASE : WEB	AROUND 59/ 41
MD Yarn	NYLON PLIED MONO 2 layers
CD Yarn	NYLON PLIED MONO 2 layers
Batt on sheet side	22& 44/55 Dtex.
Batt on roll side	44/55Dtex
Calliper at dry state	4.5-5.5 mm
Air permeability	90-120cfm
Treatment	Pre-compaction.
Elongation	About 1- 1.5%
Comments: 1: Can give felt mark on board surface 2: Good dewatering 3: Easy to clean and long life time	PURUI.